

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

Claims 1-4: (Cancelled)

BS  
5. (Original) A pneumatic tire for passenger cars comprising a rubber-steel cord composite which comprises a steel cord having, in a planar image of the composite formed by X-rays passing through the composite, a fraction R of the total area occupied by filaments of from 0.45 or more to 0.95 or less in an arbitrarily selected portion of the steel cord having a length of 15 mm in an axial direction of the cord,

wherein the length of 15 mm in an axial direction of the cord means a length of 15 mm in an axial direction of an actual cord and the fraction R of the total area occupied by the filaments is expressed as  $R=F/A$ , A representing the total area of the cord and F representing the area of the cord occupied by the filaments.

6. (Original) A pneumatic tire for passenger cars according to Claim 5, wherein the filaments of the steel cord are present substantially independently of each other in a matrix rubber.

135 7. (Original) A pneumatic tire for passenger cars according to Claim 5, wherein the steel cord has one of a  $1 \times n$  structure and a  $1+n$  structure,  $n$  being in a range of  $2 \leq n \leq 7$ .

8. (Currently Amended) A pneumatic tire for passenger cars according to Claim 5, wherein the ~~filament~~ filaments constructing the steel cord ~~has~~ have a diameter in a range of from 0.125 to 0.275 mm.

9. (Currently Amended) A pneumatic tire for passenger cars according to Claim 5, further comprising a carcass, wherein the rubber-steel cord composite is used in [[a]] the carcass layer of the pneumatic tire.

10. (Original) A pneumatic tire for passenger cars according to Claim 5, further comprising a side wall portion reinforced with a rubber reinforcing layer.

11. (Currently Amended) A pneumatic tire for passenger cars according to Claim 9, wherein the carcass comprises: a turned-up ply reinforced with a cord of an organic fiber having a melting point of 245°C or higher, and

135 a down carcass ply comprising [[a]] the rubber-steel cord composite in which a plurality of the steel cords disposed substantially parallel to each other is embedded in a matrix rubber, said down carcass ply being disposed between a side wall rubber and an outer face of the turned-up ply.

12. (Withdrawn) A pneumatic tire for passenger cars according to Claim 5, comprising

a carcass ply reinforced with polyester cords and/or polyamide cords; wherein

the rubber-steel cord composite is disposed in a side wall portion, the composite in which a plurality of steel cords disposed substantially parallel to each other is embedded in a matrix rubber.

13. (Currently Amended) A pneumatic tire for passenger cars according to Claim 9, wherein the carcass comprises a turned-up ply and a down ply, and the down ply comprises the rubber-steel cord composite in which a plurality of the steel cords disposed substantially parallel to each other [[and]] is embedded in a matrix rubber, and is disposed between a side wall portion and an outer face of the turned-up ply, and any one of the turned-up ply and the

down ply is a separate-type carcass ply which is separated into portions underneath a belt portion.

14. (Currently Amended) A pneumatic tire for passenger cars according to Claim 13, wherein any one of the turned-up ply and the down ply is separated into portions disposed under the belt portion with a distance of at least 20% of a width of the belt portion between the ply portions.